




<銅粉 代表製品>

Production process type		Type-T	Type-A	Type-B
Representative sample		5.5 $\mu\text{m}$	3.0 $\mu\text{m}$	1.5 $\mu\text{m}$
Particle Size Distribution (Dry)	D10	3.9 $\mu\text{m}$	1.8 $\mu\text{m}$	0.7 $\mu\text{m}$
	D50	5.7 $\mu\text{m}$	2.8 $\mu\text{m}$	1.5 $\mu\text{m}$
	D90	8.1 $\mu\text{m}$	3.9 $\mu\text{m}$	2.4 $\mu\text{m}$
	D99	11.2 $\mu\text{m}$	5.0 $\mu\text{m}$	3.2 $\mu\text{m}$
Specific Surface Area		0.20 $\text{m}^2/\text{g}$	0.40 $\text{m}^2/\text{g}$	0.93 $\text{m}^2/\text{g}$
TAP Density		4.8 $\text{g}/\text{cm}^3$	4.5 $\text{g}/\text{cm}^3$	3.4 $\text{g}/\text{cm}^3$
SEM	magnification	$\times 5,000$	$\times 5,000$	$\times 10,000$
				
SEM	magnification	$\times 2,000$	$\times 2,000$	$\times 5,000$
				
Particle Size Distribution chart				
		<p>5.0 <math>\mu\text{m}</math> ~ 6.5 <math>\mu\text{m}</math>      2.0 <math>\mu\text{m}</math> ~ 4.0 <math>\mu\text{m}</math>      1.5 <math>\mu\text{m}</math> ~ 3.0 <math>\mu\text{m}</math></p>		
	Particle diameter span of adjustable range	5.0 $\mu\text{m}$ ~ 6.5 $\mu\text{m}$	2.0 $\mu\text{m}$ ~ 4.0 $\mu\text{m}$	1.5 $\mu\text{m}$ ~ 3.0 $\mu\text{m}$